



Heavy Wall Heat Shrink Tubing

ORDER ONLINE



Features

- 4-foot lengths
- 3 to 1 shrink ratio
- High impact, abrasion, corrosion, and chemical resistance capable of withstanding the severe mechanical requirements of submersible and direct burial installations
- Thermoplastic Adhesive Liner provides complete environmental protection and insulation
- Meets UL 486D, CSA C22.2 No. 198.2, ANSI C119-1, Western Underground Guide Numbers 2.4, 2.5, ICEA and NEMA insulation thickness requirements
- Rated for 600 V, 90°C continuous use
- Continuous operating temperature: -55°C to 110°C
- Shrink temperature: 120°C



Technical Data

PHYSICAL PROPERTY	Test Method	Typical Performance
Tensile Strength	ASTM D412, ISO 37	2100 psi (14.5 MPa)
Elongation	ASTM D412, ISO 37	600%
Elongation after heat aging (168 hours at 175°C)	ASTM D2671, ISO 37	500% (250%)
Longitudinal change on recovery	ASTM D2671	+1%, -10%
Specific Gravity	ASTM D792	1.1
Heat shock (4 hours at 255°C)	ASTM D2671	No cracking or flowing
Low temperature flexibility (4 hours at -55°C)	ASTM D2671	No cracking or splitting
Hardness (Shore D)	ASTM D2240	50D
Oxygen Index	ASTM D2863	27.00
Flammability	ASTM D2671	Flame Retardant
ELECTRICAL PROPERTY		
Dielectric Strength	ASTM D149	500 V/Mil (20kV/mm)
Dielectric Voltage Withstand (2500V, 60Hz, 1 min.)	UL 486D	No breakdown, 24kV - 1 Min. 15kV - 4 hrs.
Volume Resistivity	ASTM D257	1016 ohm-cm
CHEMICAL PROPERTY		
Fluid Resistance	MIL-DTL-23053/15	Good to excellent
Copper Corrosion	ASTM D2671	No Corrosion
Water Absorption	ASTM D570	0.2%
Fungus Resistance	ASTM G21	No growth
ADHESIVE PROPERTY		
Adhesive softening point	ASTM E28	92°C +/- 5°C
Adhesive peel strength (300mm/min at 23°C)		
- to steel, aluminum, P.E.	ASTM D1000	35 pli
- to PVC	ASTM D1000	20 pli
Adhesive lap shear (1in./min at 23°C)	ASTM D1002	125 psi (0.875 MPa)
Adhesive Blocking (30°C)	ASTM D1146	No blocking
Adhesive water absorption	ASTM D570	less than 0.3%
Water penetration	STM 706	No penetration after 236 hrs of continuous immersion.

CFW - Heavy Wall Adhesive Lined Crosslinked Polyolefin

Part Number	Expanded Min. Internal Diameter (D)		Recovered Max. Internal Diameter (d)		Recovered Nominal Wall Thickness (w)		General use Application Range		600/1000V Single Conductor Size AWG/MCM	Standard Lengths	
	mm	IN	mm	IN	mm	IN	mm	IN		M	IN
CFW-0350-BK	8.9	0.35	3.0	0.12	1.8	0.07	3.5-8	.15-.3	14 - 10	1.2	48
CFW-0350-RD	8.9	0.35	3.0	0.12	1.8	0.07	3.5-8	.15-.3	14 - 10	1.2	48
CFW-0500-BK	13.0	0.51	4.1	0.16	2.4	0.09	4.5-11	.2-.45	8 - 6	1.2	48
CFW-0500-RD	13.0	0.51	4.1	0.16	2.4	0.09	4.5-11	.2-.45	8 - 6	1.2	48
CFW-0750-BK	19.1	0.75	6.1	0.24	2.4	0.09	6.5-16.5	.25-.65	6 - 2	1.2	48
CFW-0750-RD	19.1	0.75	6.1	0.24	2.4	0.09	6.5-16.5	.25-.65	6 - 2	1.2	48
CFW-1100-BK	27.9	1.10	8.9	0.35	3.0	0.12	10-24	.4-.95	1 - 4/0	1.2	48
CFW-1100-RD	27.9	1.10	8.9	0.35	3.0	0.12	10-24	.4-.95	1 - 4/0	1.2	48
CFW-1500-BK	38.1	1.50	11.9	0.47	4.1	0.16	13-35	.5-1.4	2/0 - 350	1.2	48
CFW-1500-RD	38.1	1.50	11.9	0.47	4.1	0.16	13-35	.5-1.4	2/0 - 350	1.2	48
CFW-2000-BK	50.8	2.00	16.0	0.63	4.1	0.16	17.5-.44	.7-1.75	250 - 500	1.2	48
CFW-2700-BK	68.1	2.70	22.1	0.87	4.1	0.16	24-59	.95-.23	600 - 100	1.2	48
CFW-3500-BK*	89.9	3.54	30.0	1.18	4.1	0.16	33-80	1.3-3.1	800 - 125	1.2	48
CFW-4700-BK*	119.9	4.72	39.9	1.57	4.2	0.17	44-104	1.75-4.1	1500 - 2500	1.2	48

*CFW 3500 and CFW 4700 are not UL or CSA Listed



Ordering Guidelines

Select a dimension which will shrink snugly over the component to be covered. If recovery is restricted the resultant wall thickness will be less than specified.

CFW Heat Shrink Tubing is available in Black (BK) and Red (RD).